TOP PROFILE BOTTOM PROFILE RUBBER COVER COLOR R18 (negative R1 (smooth) White NR70FQ diamond) **BREAKING ELONG. AT NUMBER OF TENSILE CORE STRENGTH BREAK MATERIAL PLIES** % daN/cm **EP 400** 3 ≥ 400 (UNI 8639) Polyester ≥ 22 (UNI 8639) RUBBER COVER CHARACTERISTICS **ELONG. AT BREAKING TEAR ABRASION HARDNESS RESISTANCE STRENGTH** BREAK Sh.A mm³ daN/cm² % daN/cm² ≥ 200 ≥ 500 70 ± 5 ≥ 80 90 ± 10 ISO 37; DIN 53504 ISO 34; DIN 53515 ISO 868; DIN 53505 UNI 9185 Test according to Code of Federal Regulations. Title 21, Vol 3 Rev. 01/04/2010 "Sec. 177.2600 rubber articles intended for repeated use" TESTING EXTRACTED WITH DISTILLED WATER AT REFLUX TEMPERATURE. SURFACE OF THE SAMPLE ANALYZED: 9,05 IN2 **RESULT** LIMIT **PARAMETER METHOD** mg/in² mg/in² Total extractive after 7 hours of FDA 177.2600(e) 7,84 20 extraction Total extractive after the succeeding FDA 177.2600(e) 0,14 1 2 hours of extraction TESTING EXTRACTED WITH N-HEXANE AT REFLUX TEMPERATURE. SURFACE OF THE SAMPLE ANALYZED: 9,84 IN2 **RESULT** LIMIT **PARAMETER METHOD** mg/in² mg/in² Total extractive after 7 hours of FDA 177.2600(f) 175 85,56 extraction Total extractive after the succeeding FDA 177.2600(f) 2,11 4 2 hours of extraction

FOODGRIP-NR70FQ -TSZ400



CERTIFICATE N°:38601

REMARKS: the sample conforms to the requirements for test carried out

Tests done by: CESILAB S.r.l via 9 novembre - Turbigo (MI)